



European Technical Assessment

ETA-09/0246 of 06/03/2014

Injection system BOSSONG BCR V PLUS, BOSSONG BCR V PLUS-W and BOSSONG BCR V PLUS-T for rebar connections

Post-installed rebar connections with BOSSONG BCR V PLUS, BOSSONG BCR V PLUS-W and BOSSONG BCR V PLUS-T injection mortar

Wklejane zakotwienia prętów zbrojeniowych z zaprawą iniekcyjną BOSSONG BCR V PLUS, BOSSONG BCR V PLUS-W and BOSSONG BCR V PLUS-T



Europejska Organizacja ds. Aprobat Technicznych European Organisation for Technical Approvals Europejska ocena techniczna została opracowana w Zakładzie Aprobat Technicznych przez mgr inż. Annę KUKULSKĄ-GRABOWSKĄ

Projekt okładki: Ewa Kossakowska

GW I

Kopiowanie aprobaty technicznej jest dozwolone jedynie w całości

Wykonano z oryginałów bez opracowania wydawniczego

© Copyright by Instytut Techniki Budowlanej Warszawa 2014

ISBN 978-83-249-7716-1



Dział Upowszechniania Wiedzy 02-656 Warszawa, ul. Ksawerów 21, tel.: 22 843 35 19 Format: pdf wydano w sierpniu 2014 r. zam. 636/2014



INSTYTUT TECHNIKI BUDOWLANEJ PL 00-611 WARSZAWA ul. Filtrowa 1 tel.: (+48 22) 825-04-71 (+48 22) 825-76-55 fax: (+48 22) 825-52-86 www.itb.pl





European Technical Assessment

ETA-09/0246 of 06/03/2014

General Part

| Technical Assessment Body issuing the European Technical Assessment | Instytut Techniki Budowlanej |
|--|--|
| Trade name of the construction product | Injection system BOSSONG BCR V PLUS, BOSSONG BCR V PLUS-W and BOSSONG BCR V PLUS-T for rebar connections |
| Product family to which the construction product belongs | Post-installed rebar connections with BOSSONG BCR V PLUS, BOSSONG BCR V PLUS-W and BOSSONG BCR V PLUS-T injection mortar |
| Manufacturer | BOSSONG SPA Via Enrico Fermi, 51, IT-24050 Grassobbio (Bg), Italy www.bossong.com |
| Manufacturing plant(s) | BOSSONG SPA Via Enrico Fermi, 51, IT-24050 Grassobbio (Bg), Italy |
| This European Technical Assessment contains | 22 pages including 3 Annexes which form an integral part of this assessment |
| This European Technical Assessment is issued in accordance with regulation (EU) No 305/2011, on the basis of | Guideline for European Technical Approval ETAG 001, Edition April 2013 "Metal anchors for use in concrete – Part 1: Anchors in general and Part 5: Bonded anchors", used as European Assessment Document (EAD) |
| This version replaces | ETA-09/0246 issued on 29/09/2009 |
| | |

This European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body. Any partial reproduction has to be identified as such.

Specific Part

1 Technical description of the product

The subject of this assessment are the post-installed connections, by anchoring or overlap connection joint of steel reinforcing bars (rebars) in existing structures made of normal weight concrete, using injection mortars BOSSONG BCR V PLUS, BOSSONG BCR V PLUS-W and BOSSONG BCR V PLUS-T in accordance with the regulations for reinforced concrete construction.

Reinforcing bars made of steel with diameter from 8 to 32 mm and BOSSONG BCR V PLUS, BOSSONG BCR V PLUS-W and BOSSONG BCR V PLUS-T injection mortars are used for the post-installed rebar connections. The steel element is placed into a drilled hole previously filled with a injection mortar and is anchored by the bond between embedded element, injection mortar and concrete.

An illustration and the description of the products are given in Annex A1 to A4.

2 Specification of the intended use in accordance with the applicable EAD

The performances given in Section 3 are only valid if the post-installed connections are used in compliance with the specifications and conditions given in Annex B1 to B11.

The performances given in this European Technical Assessment are based on an assumed working life of the anchor of 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer or the Technical Assessment Body, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Performance of the product

3.1.1 Mechanical resistance and stability (BWR 1)

The essential characteristic are detailed in the Annex C1 to C3.

3.1.2 Safety in case of fire (BWR 2)

No performance determined.

3.1.3 Hygiene, health and the environment (BWR 3)

Regarding the dangerous substances contained in this European Technical Assessment, there may be requirements applicable to the products falling within its scope (e.g. transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the Construction Products Regulation, these requirements need also to be complied with, when and where they apply.

3.1.4 Safety in use (BWR 4)

For basic requirement Safety in use the same criteria are valid as for Basic Requirement Mechanical resistance and stability (BR 1).

3.1.5 Sustainable use of natural resources (BWR 7)

No performance determined.

3.2 Methods used for the assessment

The assessment of fitness of the post-installed connections for the intended use in relation to the requirements for mechanical resistance and stability and safety in use in the sense of the Basic Requirements 1 and 4 has been made in accordance with the ETAG 001 *"Metal anchors for use in concrete*", Part 1: *"Anchors in general"* and Part 5: *"Bonded anchors"* and EOTA Technical Report TR 023 *"Assessment of post-installed rebar connections"*.

4 Assessment and verification of constancy of performance (hereinafter AVCP) system applied, with reference to its legal base

According to Decision 96/582/EC of the European Commission the system of assessment and verification of constancy of performance (see Annex V to Regulation (EU) No 305/2011) is system 1.

| Product | Intended use | Level or class | System |
|-----------------------------------|---|----------------|--------|
| Metal anchors for use in concrete | For fixing and/or supporting to concrete structural elements (which contributes to the stability of the works) or heavy units | _ | 1 |

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at Instytut Techniki Budowlanej.

For initial type testing the results of the tests performed as part of the assessment for the European Technical Assessment shall be used unless there are changes in the production line or plant. In such cases the necessary initial type testing has to be agreed between Instytut Techniki Budowlanej and the notified body.

Issued in Warsaw on 06/03/2014 by Instytut Techniki Budowlanej

Joh

Jan Bobrowicz Director of ITB





| Table | Δ1۰ | Rebars | |
|-------|----------------|----------|--|
| Iabic | ~ · · · | ILCDUI 3 | |

| Designation | Rebars |
|---|---|
| Rebars according to EN 1992-1-1, Annex C, Table C.1 and C.2N | Bars and de-coiled rods Class B or C Minimum relative rib area, $f_{R,min}$, according to EN 1992-1-1 The rib height h: h ≤ 0,07 · Ø |

Table A2: Injection mortars

| Designation | Composition |
|---|---|
| BOSSONG BCR V PLUS BOSSONG BCR V PLUS-W BOSSONG BCR V PLUS-T (two component injection mortars) | Additive: quartz Bonding agent: vinyl ester resin styrene free Hardener: dibenzoyl peroxide |

Injection system BOSSONG BCR V PLUS, BOSSONG BCR V PLUS-W and BOSSONG BCR V PLUS-T for rebar connections

Materials

Annex A3

of European Technical Assessment ETA-09/0246



SPECIFICATION OF INTENDED USE

Anchorages subject to:

Static and quasi-static loads.

Base material:

- Reinforced or unreinforced normal weight concrete of strength class C12/15 at minimum to C50/60 at maximum according to EN 206-1.
- Maximum chloride content of 0,20% (Cl 0,20) related to the cement content according to EN 206-1.
- Non-carbonated concrete.

Note: In case of a carbonated surface of the existing concrete structure the carbonate layer shall be removed in the area of the post-installed rebar connection with a diameter of $d_s + 60$ mm prior to the installation of the new rebar. The depth of concrete to be removed shall correspond to at least the minimum concrete cover according to EN 1992-1-1. The above may be neglected if building components are new and not carbonated and if building components are in dry conditions.

Temperature range:

The products may be used in the following temperature range:

-40°C to +80°C (max. short term temperature +80°C and max. long term temperature +50°C).

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions.
- Structures subject to external atmospheric exposure including industrial and marine environment.
- Structures subject to permanently damp internal conditions if no particular aggressive conditions exist.

Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used).

Design:

- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking into account of the forces to be transmitted.
- Design according to EN 1992-1-1 and Annex B2.
- The actual position of the reinforcement in the existing structure shall be determined on the basis of the construction documentation and taken into account when designing.

Installation:

- Dry or wet concrete (use category 1).
- It must not be installed in flooded holes.
- Overhead installation is permissible.
- Hole drilling by hammer drill.
- Installation of the post-installed rebars shall be done only by suitable trained installer and under supervision on the site.
- Check the position of the existing rebars (if the position of existing rebars in not known it shall be determined using a rebar detector suitable for this purpose as well as on the basis of the construction documentation and then marked on the building component for the overlap joint).

Injection system BOSSONG BCR V PLUS, BOSSONG BCR V PLUS-W and BOSSONG BCR V PLUS-T for rebar connections

Annex B1

of European Technical Assessment ETA-09/0246

Intended use. Specification



| Γable B1: Installation data – hammer drilling | | | | | | | | | |
|---|-----|-----|-----|-----|-----|------|------|------|------|
| Rebar diameter [mm] Ø8 Ø10 Ø12 Ø14 Ø16 Ø20 Ø25 Ø28 Ø3 | | | | | | | | | Ø32 |
| Drill bit diameter [mm] | 12 | 14 | 16 | 18 | 20 | 25 | 30 | 35 | 40 |
| Brush diameter [mm] | 14 | 16 | 18 | 20 | 22 | 27 | 32 | 37 | 42 |
| Minimum anchorage length I _{b,min} [mm] | 115 | 145 | 170 | 200 | 230 | 285 | 355 | 400 | 455 |
| Minimum anchorage length l _{o,min} - overlap joint [mm] | 200 | 200 | 200 | 210 | 240 | 300 | 375 | 420 | 480 |
| Maximum embedment depth I _{v,max} [mm] | 400 | 500 | 600 | 700 | 800 | 1000 | 1000 | 1000 | 1000 |

Note: $I_{b,min}$ and $I_{0,min}$ according to EN 1992-1-1 (8.6) and (8.11) with: yield stress for rebar 500 N/mm²; $\gamma_M = 1,15$; $\alpha_6 = 1,0$; concrete C20/25 and $f_{bd} = 2,30$ N/mm² (good bond conditions)

Minimum concrete cover (see Annex B2):

 c_{min} = 30 mm + 0,06 · $I_v \ge 2 \cdot Ø$ for Ø < 25 mm

 c_{min} = 40 mm + 0,06 \cdot I_v ≥ 2 \cdot Ø for Ø \geq 25 mm

The minimum concrete cover according to EN 1992-1-1 shall be observed.

Minimum clear spacing between two post-installed rebars:

 $a = 40 \text{ mm} \ge 4 \cdot \emptyset$

Injection system BOSSONG BCR V PLUS, BOSSONG BCR V PLUS-W and BOSSONG BCR V PLUS-T for rebar connections

Annex B3

of European Technical Assessment ETA-09/0246

Installation data

| able B2: Processing time and minimum curing time | | | | | | | | | |
|--|---|-----|--|--|--|--|--|--|--|
| BOSSONG | BOSSONG BCR V PLUS (standard version) | | | | | | | | |
| Concrete temperature [C°] | Concrete temperature [C°] Processing time [min.] Minimum curing time ¹⁾ [min.] | | | | | | | | |
| -5 | 65 | 780 | | | | | | | |
| 0 | 45 | 420 | | | | | | | |
| +5 | 25 | 90 | | | | | | | |
| +10 | 16 | 60 | | | | | | | |
| +15 | 11,5 | 45 | | | | | | | |
| +20 | 7,5 | 40 | | | | | | | |
| +25 | 5 | 35 | | | | | | | |
| +30 | 3 | 30 | | | | | | | |
| +35 | 2 | 25 | | | | | | | |
| +40 | 1 | 20 | | | | | | | |

BOSSONG BCR V PLUS-W (version for winter season)

| Concrete temperature [C°] | Processing time [min.] | Minimum curing time ¹⁾ [min.] |
|---------------------------|------------------------|--|
| -5 | 40 | 210 |
| 0 | 25 | 100 |
| +5 | 15 | 70 |
| +10 | 10 | 50 |
| +15 | 7 | 35 |
| +20 | 5 | 30 |

| BOSSONG BCR V PLUS-T (version for summer season) | | | | | | | | | |
|--|---|----|--|--|--|--|--|--|--|
| Concrete temperature [C°] | Concrete temperature [C°] Processing time [min.] Minimum curing time ¹⁾ [min.] | | | | | | | | |
| +20 | 14 | 60 | | | | | | | |
| +25 | 11 | 50 | | | | | | | |
| +30 | 8 | 40 | | | | | | | |
| +35 | 6 | 30 | | | | | | | |
| +40 | 4 | 20 | | | | | | | |
| +45 | 3 | 20 | | | | | | | |
| +50 | 2 | 20 | | | | | | | |

¹⁾ The minimum time from the end of the mixing to the time when the rebar may be loaded. Minimum resin temperature for installation +5°C. Maximum resin temperature for installation +30°C. For wet condition the curing time must be double.

Injection system BOSSONG BCR V PLUS, BOSSONG BCR V PLUS-W and BOSSONG BCR V PLUS-T for rebar connections

Annex B4

of European Technical Assessment ETA-09/0246

Processing time and curing time





Table B4: Special brush details (mechanical brush)

| Rebar diameter [mm] | | | | Ø10 | Ø12 | Ø14 | Ø16 | Ø20 | Ø25 | Ø28 | Ø32 |
|---------------------|--------------------|------|----|-----|-----|-----|-----|-----|-----|-----|-----|
| d ₀ | Nominal drill hole | [mm] | 12 | 14 | 16 | 18 | 20 | 25 | 30 | 35 | 40 |
| d _b | Brush diameter | [mm] | 14 | 16 | 18 | 20 | 22 | 27 | 32 | 37 | 42 |

Injection system BOSSONG BCR V PLUS, BOSSONG BCR V PLUS-W and BOSSONG BCR V PLUS-T for rebar connections

Annex B6

of European Technical Assessment ETA-09/0246

Cleaning tools (2)



| Pumps (injection guns) | Cartridges | Clean hole tools | Maximum depth of the drill hole |
|---|---|---|------------------------------------|
| Manual | 825 ml | Blower pump or compressed air and standard brush or special brush | 300 mm |
| Manual | 400 ml 380 ml | Blower pump or compressed air and standard brush or special brush | 300 mm |
| Manual | 345 ml 300 ml 165 ml | Blower pump or compressed air and standard brush or special brush | 300 mm |
| Manual | 300 ml 165 ml | Blower pump or compressed air and standard brush or special brush | 300 mm |
| Proumatio | 825 ml | Compressed air and special brush | 300 mm to 1000 mm* |
| Pneumatic | 400 ml 380 ml | Compressed air and special brush | 300 mm to 1 1000 mm* |
| Note: use the mixer extension describe | d in Annex B7 for | the injection of the m | lortar |
| Injection system BOSSC OSSONG BCR V PLUS-W and I for rebar conn | Annex B8 | | |
| Tools for install | of European Technical Assessr ETA-09/0246 | | |







| Rebar | Ultimate bond resistance f _{bd} ¹ [N/mm ²] | | | | | | | | | |
|-------|--|--------|-------|--------|--------|--------|--------|--------|--------|--|
| [mm] | C12/15 | C16/20 | 20/25 | C25/30 | C30/37 | C35/45 | C40/50 | C45/55 | C50/60 | |
| Ø8 | 1,60 | 2,00 | 2,30 | 2,70 | 3,00 | 3,40 | 3,70 | 4,00 | 4,30 | |
| Ø10 | 1,60 | 2,00 | 2,30 | 2,70 | 3,00 | 3,40 | 3,70 | 4,00 | 4,30 | |
| Ø12 | 1,60 | 2,00 | 2,30 | 2,70 | 3,00 | 3,40 | 3,70 | 4,00 | 4,30 | |
| Ø14 | 1,60 | 2,00 | 2,30 | 2,70 | 3,00 | 3,40 | 3,70 | 4,00 | 4,30 | |
| Ø16 | 1,60 | 2,00 | 2,30 | 2,70 | 3,00 | 3,40 | 3,70 | 4,00 | 4,00 | |
| Ø20 | 1,60 | 2,00 | 2,30 | 2,70 | 3,00 | 3,40 | 3,70 | 4,00 | 4,00 | |
| Ø25 | 1,60 | 2,00 | 2,30 | 2,70 | 3,00 | 3,40 | 3,70 | 3,70 | 3,70 | |
| Ø28 | 1,60 | 2,00 | 2,30 | 2,70 | 3,00 | 3,40 | 3,40 | 3,40 | 3,40 | |
| Ø32 | 1,60 | 2,00 | 2,30 | 2,70 | 2,70 | 2,70 | 2,70 | 2,70 | 2,70 | |

| Table | C1. | Design | values | of the | ultimate | bond | resistance | f _{bd} according | g to | ΕN | 1992-1-1 |
|--------|-----|-------------|--------|--------|----------|------|------------|---------------------------|------|----|----------|
| for ha | mme | er drilling | 9 | | | | | | | | |

¹ The values given are valid for good bond condition according to EN 1992-1-1. For all other bond conditions multiply the value by 0,7.

Injection system BOSSONG BCR V PLUS, BOSSONG BCR V PLUS-W and BOSSONG BCR V PLUS-T for rebar connections

Annex C1

of European Technical Assessment ETA-09/0246

Design values of the ultimate bond resistance

| Rebar Ø | e load 00 | a | $\alpha_1 = \alpha_2 = \alpha_3 = \alpha_4 = \alpha_5 = \alpha_5$ | 1,0 | $\alpha_1 = \alpha_3 = \alpha_4 = 1,0$ and α_2 or $\alpha_5 = 0,7$ | | | |
|---------|-----------------------|---|---|-----------------|---|--------------|-----------------|--|
| | Tensil B5 | Anchorage length I _{bd} ¹⁾ | Tension load | Mortar volume V | Anchorage length l _{bd} ¹⁾ | Tension load | Mortar volume V | |
| [mm] | [kN] | [mm] | [kN] | [ml] | [mm] | [kN] | [ml] | |
| 8 | | 115 | 6,65 | 8,50 | 115 | 9,50 | 8,50 | |
| | | 180 | 10,40 | 13,31 | 180 | 14,86 | 13,31 | |
| | 21,85 | 250 | 14,45 | 18,48 | 200 | 16,52 | 14,78 | |
| | | 320 | 18,50 | 23,65 220 | | 18,17 | 16,26 | |
| | | 378 | 21,85 | 27,95 | 265 | 21,85 | 19,56 | |
| | | 145 | 10,48 | 12,86 | 145 | 14,97 | 12,86 | |
| | Γ | 230 | 16,62 | 20,40 | 230 | 23,74 | 20,40 | |
| 10 | 34,15 | 310 | 22,40 | 27,50 | 260 | 26,84 | 23,06 | |
| | [| 390 | 28,18 | 34,59 | 290 | 29,93 | 25,72 | |
| | | 473 | 34,15 | 41,92 | 331 | 34,15 | 29,34 | |
| | | 170 | 14,74 | 17,59 | 170 | 21,06 | 17,59 | |
| 12 | | 270 | 23,41 | 27,94 | 270 | 33,44 | 27,94 | |
| | 49,17 | 370 | 32,08 | 38,29 | 300 | 37,16 | 31,05 | |
| | | 470 | 40,75 | 48,64 | 330 | 40,88 | 34,15 | |
| | | 567 | 49,17 | 58,69 | 397 | 49,17 | 41,08 | |
| | | 200 | 20,23 | 23,65 | 200 | 28,90 | 23,65 | |
| | | 320 | 32,37 | 37,85 | 320 | 46,24 | 37,85 | |
| 14 | 66,93 | 440 | 44,51 | 52,04 | 360 | 52,02 | 42,58 | |
| | | 560 | 56,65 | 66,23 | 400 | 57,81 | 47,31 | |
| | | 662 | 66,93 | 78,25 | 463 | 66,93 | 54,78 | |
| | | 230 | 26,59 | 30,60 | 230 | 37,99 | 30,60 | |
| | | 360 | 41,62 | 47,90 | 360 | 59,46 | 47,90 | |
| 16 | 87,42 | 490 | 56,65 | 65,20 | 400 | 66,06 | 53,22 | |
| | | 620 | 71,68 | 82,49 | 440 | 72,67 | 58,54 | |
| | | 756 | 87,42 | 100,61 | 529 | 87,42 | 70,43 | |
| 20 | | 285 | 41,19 | 59,25 | 285 | 58,84 | 59,25 | |
| | | 450 | 65,03 | 93,55 | 450 | 92,90 | 93,55 | |
| | 136,59 | 620 | 89,60 | 128,90 | 500 | 103,22 | 103,95 | |
| | | 790 | 114,17 | 164,24 | 550 | 113,55 | 114,34 | |
| | | 945 | 136,59 | 196,50 | 662 | 136,59 | 137,55 | |
| 25 | | 355 | 64,13 | 90,21 | 355 | 91,61 | 90,21 | |
| | | 520 | 93,93 | 132,13 | 520 | 134,19 | 132,13 | |
| | 213,42 | 680 | 122,84 | 172,79 | 600 | 154,84 | 152,46 | |
| | | 840 | 151,74 | 213,44 | 650 | 167,74 | 165,16 | |
| | | 1000 | 180,64 | 254,10 | 700 | 180,64 | 177,87 | |
| 28 | | 400 | 80,93 | 162,99 | 400 | 115,61 | 162,99 | |
| | | 550 | 111,28 | 224,12 | 550 | 158,96 | 224,12 | |
| | 267,72 | 700 | 141,62 | 285,24 | 700 | 202,32 | 285,24 | |
| | | 850 | 171,97 | 346,36 | 850 | 245,67 | 346,36 | |
| | | 1000 | 202,32 | 407,48 | 926 | 267,72 | 377,44 | |
| | <u>† † †</u> | 455 | 105,21 | 242,16 | 455 | 150,29 | 242,16 | |
| | | 590 | 136,42 | 314,01 | 500 | 165,16 | 266,11 | |
| 32 | 349,67 | 730 | 168,79 | 388,52 | 550 | 181,67 | 292,72 | |
| 32 | | 870 | 201 16 | 462.02 | 600 | 108 10 | 310.33 | |

The given values are valid for good bond condition according to EN 1992-1-1. For all other bond condition the values for tension load shall be multiplied by 0,7. The mortar volume V can be calculated using the equation: $V = I_{bd} \cdot \pi \cdot (d_0^2 \cdot d^2) / (4 \cdot 0.85)$ with the nominal hole diameter.

Injection system BOSSONG BCR V PLUS, BOSSONG BCR V PLUS-W and BOSSONG BCR V PLUS-T for rebar connections

Annex C2

Design values for anchoring connections

of European Technical Assessment ETA-09/0246 Γ

| Rebar Ø | e load 00 | a | $\alpha_1 = \alpha_2 = \alpha_3 = \alpha_5 = \alpha_6$ | = 1,0 | $\alpha_1 = \alpha_3 = \alpha_6 = 1,0$ and α_2 or $\alpha_5 = 0,7$ | | | |
|------------------|---------------------------------|---|--|--|---|---|-------------------------------------|--|
| | Tensile B5(| Lap splice length l ₀ ¹⁾ | Tension load | Mortar volume V | Lap splice length I ₀ ¹⁾ | Tension load | Mortar volume V | |
| nm] | [kN] | [mm] | [kN] | [ml] | [mm] | [kN] | [ml] | |
| | | 200 | 11,56 | 14,78 | 200 | 16,52 | 14,78 | |
| | 04.05 | 240 | 13,87 | 17,74 | - | - | - | |
| 8 | 21,85 | 280 | 16,19 | 20,70 | - | - | | |
| | - | 378 | 21,85 | 27,95 | - | - | - | |
| | | 200 | 14,45 | 17,74 | 200 | 20,64 | 17,74 | |
| | | 270 | 19,51 | 23,95 | 235 | 24,26 | 20,85 | |
| 0 | 34,15 | 340 | 24,57 | 30,16 | 270 | 27,87 | 23,95 | |
| | | 410 | 29,03 | 41.92 | 331 | 34 15 | 21,00 | |
| | | 200 | 17,34 | 20,70 | 200 | 24,77 | 20,70 | |
| | | 290 | 25,15 | 30,01 | 250 | 30,97 | 25,87 | |
| 2 | 49,17 | 380 | 32,95 | 39,33 | 300 | 37,16 | 31,05 | |
| | - | 470 | 40,75 | 48,64 | 350 | 43,35 | 36,22 | |
| | | 210 | 21 24 | 24 84 | 210 | 30.35 | 24 84 | |
| | | 320 | 32,37 | 37,85 | 270 | 39,02 | 31,93 | |
| 4 | 66,93 | 430 | 43,50 | 50,86 | 330 | 47,69 | 39,03 | |
| | - | 540 | 54,63 | 63,87 | 390 | 56,36 | 46,13 | |
| | | 662 240 | 66,93 27.75 | 78,25 | 463 240 | 66,93 39.64 | 54,78 31.93 | |
| | - | 370 | 42,78 | 49,23 | 310 | 51,20 | 41,25 | |
| 6 | 87,42 | 500 | 57,81 | 66,53 | 380 | 62,76 | 50,56 | |
| | | 630 | 72,83 | 83,83 | 450 | 74,32 | 59,88 | |
| | | 756 | 87,42 | 100,61 | 529 | 87,42 | 70,43 | |
| | | 460 | 43,35 | 95.63 | 390 | 80.51 | 81.08 | |
| 20 | 136,59 | 620 | 89,60 | 128,90 | 480 | 99,09 | 99,79 | |
| | | 780 | 112,72 | 162,16 | 570 | 117,68 | 118,50 | |
| | | 945 | 136,59 | 196,50 | 662 | 136,59 | 137,55 | |
| | - | 530 | 67,74 95.74 | 95,29 134.67 | 670 | 96,77 | 95,29 170,25 | |
| 25 | 213,42 | 690 | 124,64 | 175,33 | 780 | 201,29 | 198,20 | |
| | - / | 850 | 153,55 | 215,98 | 800 | 206,45 | 203,28 | |
| | | 1000 | 180,64 | 254,10 | 827 | 213,42 | 210,14 | |
| | - | 420 | 84,97 | 1/1,14 | 420 | 121,39 | 1/1,14 | |
| 28 | 267,72 | 720 | 145.67 | 293.39 | 810 | 234.11 | 330.06 | |
| | | 870 | 176,02 | 354,51 | 900 | 260,12 | 366,73 | |
| | | 1000 | 202,32 | 407,48 | 926 | 267,72 | 377,44 | |
| | - | 480 | 110,99 | 255,47 | 480 | 158,55 | 255,47 | |
| 2 | 349.67 | 740 | 141,04 | 393.84 | 740 | 201,49 | 393 84 | |
| 02 | 040,01 | 870 | 201,16 | 463,03 | 870 | 287,37 | 463,03 | |
| | | 1000 | 231,22 | 532,22 | 1000 | 330,32 | 532,22 | |
| given tiplied | values are va by 0,7. The mo | alid for good bond ortar volume V can | condition according be calculated using t | to EN 1992-1-1. For al he equation: V = I _{bd} · π · | other bond condi $(d_0^2 - d^2) / (4 \cdot 0.85)$ | tion the values for t with the nominal hol | ension load shall be e diameter. | |
| В | Inj OSSONG | ection syst BCR V PLI | em BOSSON US-W and BO | IG BCR V PLU DSSONG BCR | S, V PLUS-T | | Annex C3 | |



ISBN 978-83-249-7716-1